

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 000 969 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
09.10.2002 Bulletin 2002/41

(51) Int Cl.7: **C08K 5/50, C08K 5/42,
C08K 5/00, C08K 5/103**

(21) Application number: **99308837.6**

(22) Date of filing: **05.11.1999**

(54) **Antistatic agent for synthetic polymer materials and method of application thereof**

Antistatikummittel für syntetische Polymermaterialien und dessen Anwendungsmethode

Agent antistatique pour matière polymère synthétique et sa méthode d'utilisation

(84) Designated Contracting States:
DE FR GB IT

(30) Priority: **12.11.1998 JP 32117698
08.10.1999 JP 28747099**

(43) Date of publication of application:
17.05.2000 Bulletin 2000/20

(73) Proprietor: **Takemoto Yushi Kabushiki Kaisha
Gamagouri-shi Aichi-ken (JP)**

(72) Inventor: **Suzuki, Masahiro,
c/o Takemoto Yushi KK
Gamagouri-shi, Aichi-ken (JP)**

(74) Representative: **Ablewhite, Alan James
MARKS & CLERK,
57/60 Lincoln's Inn Fields
London WC2A 3LS (GB)**

(56) References cited:
US-A- 4 943 380 US-A- 5 449 709

EP 1 000 969 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**Background of the Invention**

5 [0001] This invention relates to antistatic agents for synthetic polymer materials and methods of applying such an antistatic agent to a synthetic polymer material. Synthetic polymer materials are usually strongly hydrophobic and hence tend to become electrostatically charged. These characteristics are a problem in the production process of such materials as well as when the products made therefrom are actually used. This invention relates to antistatic agents with which such problem can be overcome and also to a method of applying such an agent to a synthetic polymer material.

10 [0002] In the past, electrically conductive agents such as carbon or electrically conductive metallic powder or surfactants used to be used as an antistatic agent against synthetic polymer materials. They are usually added to such a synthetic polymer material or applied on its surface. When such an electrically conductive agent is used, however, a significantly large quantity is usually required for obtaining any appreciable effect and the method of application was not very simple. Moreover, since transparent products of this kind were hard to obtain and these agents are rather expensive, they could be used only under limited circumstances. On the other hand, there are many kinds of surfactants and it is usually possible to select an appropriate surfactant for most situations, and many kinds have been proposed for application to synthetic polymer materials. If an anionic surfactant is used, however, its compatibility is usually poor and it may not disperse uniformly. Since it tends to decompose or deteriorate when heated and to adversely affect hue or transparency, it is considered difficult to use. Cationic surfactants having quaternary nitrogen in the molecule or amphoteric surfactants have good antistatic capabilities but their resistance against heat is poor, and hence they can be used only for a limited range of purposes. Non-ionic surfactants are superior to ionic surfactants regarding compatibility with synthetic polymer materials but not only is their antistatic capability weak but it tends to become weaker with time at normal or higher temperatures. For improving the characteristics of these surfactants, Japanese Patent Publications Tokkai 62-230835, 63-117061, 1-14267, 1-62336 and 1-92474 and U.S. patent 4,943,380 have proposed the use of phosphonium sulfonates. The kinds of phosphonium sulfonates proposed in these references, however, tend to adversely affect the natural hue or transparency of the synthetic polymer materials, and since only a limited amount of them can be used, sufficient antistatic quality cannot be obtained under a low humidity condition.

30 **Summary of the Invention**


[0003] The problem, to which the present invention is addressed, is that prior art phosphonium sulfonates affect the natural hue and transparency of synthetic polymer materials and since they cannot be used in a sufficiently large amount that their antistatic capabilities are limited under a low humidity condition although they generally have better compatibility and resistance against heat than other kinds of surfactants.

35 [0004] The invention is based on the inventor's discovery that the above and other problems can be successfully addressed to if use is made of a specified kind of phosphonium sulfonate and a specified kind of inorganic sulfonate are used in combination as an antistatic agent for synthetic polymer materials.

40 **Detailed Description of the Invention**

[0005] This invention relates to an antistatic agent for synthetic polymer materials characterized as comprising a phosphonium sulfonate shown by Formula (1) below:

45




50

Formula (1)

and an inorganic sulfonate shown by Formula (2) below:

55

**Formula (2)**

where A¹ and A² are each independently an alkyl group with 1-36 carbon atoms, an alkenyl group with 4-24 carbon atoms, a phenyl group, a phenyl group substituted by an alkyl group with 1-18 carbon atoms, a naphthyl group or a naphthyl group substituted by an alkyl group with 1-18 carbon atoms; R¹, R², R³ and R⁴ are each independently an aliphatic or aromatic hydrocarbon group with 1-18 carbon atoms or a hydrocarbon group substituted by a hydroxyl or cyano group, Mⁿ⁺ is an alkali metal cation if n = 1 and an alkaline-earth metal cation if n = 2; and n = 1 or 2.

[0006] This invention also relates to an antistatic agent for synthetic polymer materials characterized as comprising not only a phosphonium sulfonate shown by Formula (1) given above and an inorganic sulfonate shown by Formula (2) given above, but also aliphatic carboxylic acid ester of polyhydric alcohol.

[0007] This invention further relates to a method of providing an antistatic characteristic to a synthetic polymer material by adding a phosphonium sulfonate shown by Formula (1) given above and an inorganic sulfonate shown by Formula (2) given above.

[0008] This invention still further relates to a method of providing an antistatic characteristic to a synthetic polymer material by adding not only a phosphonium sulfonate shown by Formula (1) given above and an inorganic sulfonate shown by Formula (2) given above but also aliphatic carboxylic acid ester of polyhydric alcohol.

[0009] Phosphonium sulfonate shown by Formula (1) is characterized as comprising both organic sulfonate anion and organic phosphonium cation. Examples of such organic sulfonate anion include (1) those having alkyl group with 1-36 carbon atoms such as methyl sulfonate, ethyl sulfonate, propyl sulfonate, butyl sulfonate, octyl sulfonate, dodecyl sulfonate, tetradecyl sulfonate, stearyl sulfonate, tetracosyl sulfonate and 2-ethylhexyl sulfonate, (2) those having alkenyl group with 4-24 carbon atoms such as butenyl sulfonate, octenyl sulfonate, dodecenyl sulfonate, tetradecenyl sulfonate and octadecenyl sulfonate; (3) phenyl sulfonate; (4) those having phenyl group substituted by alkyl group with 1-18 carbon atoms such as methylphenyl sulfonate, butylphenyl sulfonate, octylphenyl sulfonate, dodecylphenyl sulfonate, dibutylphenyl sulfonate and dinonylphenyl sulfonate; (5) naphthyl sulfonate; and (6) those having naphthyl group substituted by alkyl group with 1-18 carbon atoms such as diisopropyl naphthyl sulfonate and dibutyl naphthyl sulfonate. Preferable among these are those having alkyl group with 6-22 carbon atoms, those having phenyl group substituted by alkyl group with 2-12 carbon atoms and those having naphthyl group substituted by alkyl group with 2-12 carbon atoms. Dodecylbenzene sulfonate anion is particularly preferable.

[0010] Examples of organic phosphonium cation of Formula (1) include (1) those wherein R¹ - R⁴ in Formula (1) are each aliphatic hydrocarbon group with 1-18 carbon atoms such as tetramethyl phosphonium, tetraethyl phosphonium, tetrabutyl phosphonium, triethylmethyl phosphonium, tributylmethyl phosphonium, diethyl-diethyl phosphonium, diocetyl-dimethyl phosphonium, trimethylbutyl phosphonium, trimethyloctyl phosphonium, trimethyl-lauryl phosphonium, trimethyl-stearyl phosphonium, triethyloctyl phosphonium and tributyoctyl phosphonium; (2) those wherein at least one of R¹ - R⁴ is aromatic hydrocarbon group such as tetraphenyl phosphonium, triphenyl methyl phosphonium, triphenylethyl phosphonium, triphenylbenzyl phosphonium and tributylbenzyl phosphonium; and (3) those wherein at least one of R¹ - R⁴ is hydrocarbon group substituted by hydroxyl group or cyano group such as tetramethylol phosphonium, tri (2-cyanoethyl) methyl phosphonium, tri (2-cyanoethyl) benzyl phosphonium, tri (3-hydroxypropyl) methyl phosphonium, tri (3-hydroxypropyl) benzyl phosphonium, trimethyl (2-hydroxyethyl) phosphonium and tri (2-hydroxyethyl) methyl phosphonium. Preferable among these are organic phosphonium cations wherein R¹ - R⁴ in Formula (1) are each aliphatic hydrocarbon group with 1-8 carbon atoms. Tetrabutyl phosphonium cation is particularly preferred.

[0011] The invention does not impose any particular limitation on the combination of organic sulfonate anion and organic phosphonium cation. These phosphonium sulfonates can be obtained by mixing corresponding metallic or ammonium salt of the organic sulfonate and quaternary phosphonium salt inside a solvent and separating the by-product inorganic salt by rinsing or extracting the phosphonium sulfonate by using an organic solvent such as methanol, isopropanol or acetone.

[0012] The inorganic sulfonates shown by Formula (2) are metallic salts obtained by using the same organic sulfonate anion described above regarding phosphonium sulfonates shown by Formula (1). Preferred alkali metallic salts include salts of sodium and potassium. Preferred alkaline-earth metallic salts include salts of calcium and magnesium.

[0013] Examples of aliphatic carboxylic acid ester of polyhydric alcohol which may be used according to this invention together with phosphonium sulfonate shown by Formula (1) and inorganic sulfonate shown by Formula (2) include ethylene glycol, propylene glycol, glycerol, polyglycerols having degree of polymerization 2-10 such as diglycerol and triglycerol, alkylene oxide adducts of these polyglycerols, and monoesters, diesters and triesters of polyhydric (dihydric - pentahydric) alcohol such as trimethylol propane and pentaerythritol and aliphatic carboxylic acid with 8-24 carbon atoms such as octanoic acid, lauric acid, stearic acid and behenic acid. Preferable among them are esters of glycerol, polyglycerol with degree of polymerization 2-10, trimethylolpropane or pentaerythritol with an aliphatic carboxylic acid. Glycerol monostearate, diglycerol monostearate and pentaerythritol distearate are particularly preferred.

[0014] The antistatic agents of this invention are not limited by the method of their production. Examples of production method include: (1) the method of separately synthesizing a phosphonium sulfonate shown by Formula (1) and an inorganic sulfonate shown by Formula (2) and then mixing them together; (2) the method of preparing a mixture of a phosphonium sulfonate shown by Formula (1) and an inorganic sulfonate shown by Formula (2) by reacting respectively

corresponding inorganic sulfonate and phosphonium halide at a molar ratio ((sulfonate)/(halide)) greater than 1; (3) the method of preparing a mixture of a phosphonium sulfonate shown by Formula (1) and an inorganic sulfonate shown by Formula (2) by a neutralization reaction in which an alkali compound such as alkali metal oxide, alkali metal carbonate, alkali metal hydrogencarbonate, alkaline-earth metal oxide, alkaline-earth metal carbonate or alkaline-earth hydrogencarbonate and a corresponding phosphonium hydroxide together with a corresponding organic sulfonic acid; and (4) the method of further mixing aliphatic carboxylic acid ester of polyhydric alcohol to the mixture obtained in (1)-(3).

[0015] As stated above, antistatic agents of this invention include both those with two components consisting of phosphonium sulfonate shown by Formula (1) and inorganic sulfonate shown by Formula (2) and those with three components further including aliphatic carboxylic acid ester of polyhydric alcohol. The invention does not impose any stringent limitation on the ratio of mixture for either type but the weight ratio between the phosphonium sulfonate of Formula (1) and the inorganic sulfonate of Formula (2) is preferably 99/1 - 5/95. Ratios in the range of 98/2 - 20/80 are more preferable and those in the range of 95/5 - 25/75 are even more preferable. As for the weight ratio between the sum of the phosphonium sulfonate of Formula (1) and the inorganic sulfonate of Formula (2) with respect to the aliphatic carboxylic acid ester of polyhydric alcohol, those in the range of 95/5 - 10/90 are preferable, those in the range of 80/20 - 20/80 are more preferable and those in the range of 70/30 - 30/70 are even more preferable. With the mixing ratio within such a range, antistatic agents of this invention can demonstrate their antistatic characteristics more prominently.

[0016] Methods according to this invention of applying an antistatic agent to a synthetic polymer material are categorized into (1) methods of adding any of those agents described above with two components and (2) method of adding any of those agents described above with three components. Methods of this invention are not stringently limited as to the ratio by which these two or three components are added, but the preferred ratios are as explained above. Thus, it is preferable to add phosphonium sulfonate of Formula (1) and inorganic sulfonate of Formula (2) at a weight ratio in the range of 99/1 - 5/95, more preferably in the range of 98/2 - 20/80 and even more preferably in the range of 95/5 - 25/75. When all three components are added, the weight ratio between the sum of phosphonium sulfonate of Formula (1) and inorganic sulfonate of Formula (2) to aliphatic carboxylic acid ester of polyhydric alcohol is preferably in the range of 95/5 - 10/90, more preferably in the range of 80/20 - 20/80, and even more preferably in the range of 70/30 - 30/70. By a method of application according to this invention as limited above, it is possible to provide a superior antistatic characteristic to a synthetic polymer material.

[0017] The invention does not impose any particular limitation on the method of applying or adding components of an antistatic agent to a synthetic polymer material. Examples of the method include (1) those wherein the two or three components of an antistatic agent according to this invention are preliminarily mixed together to form a mixture and this mixture is added to the synthetic polymer material; and (2) those wherein these two or three components are separately added to the synthetic polymer material. In the latter case, the order of addition is not important.

[0018] Examples of method for adding each component of an antistatic agent of this invention to a synthetic polymer material include (1) those of adding these components during the polymerization process for producing the synthetic polymer material; and (2) those of adding them during the molding of the synthetic polymer material.

[0019] Neither does this invention impose any particular limitation as to the amount of each component of an antistatic agent of this invention to be added to a synthetic polymer material. It is generally preferable, however, that the total amount of the components to be added will be 0.1 - 10 weight parts, and more preferably 0.2 - 4 weight parts, to 100 weight parts of the synthetic polymer material.

[0020] Examples of synthetic polymer materials to which antistatic agents of this invention can be effectively applied include (1) polyolefin resins such as polyethylene resins and polypropylene resins; (2) polycarbonate resins; (3) polyester resins such as polyethylene terephthalate and polybutylene terephthalate; (4) polymethyl methacrylate resins; and (5) polycaprolactam resins. The effects are particularly prominent when applied to polycarbonate resins, polyester resins and polymethyl methacrylate resins, and even more particularly prominent when applied to polycarbonate resins.

[0021] When a method of providing antistatic characteristic is used for polycarbonate resin, it is preferable to apply 0.5 - 2.0 weight parts of phosphonium sulfonate of Formula (1) to 100 weight parts of the resin, 0.02 - 0.1 weight part of inorganic sulfonate of Formula (2) and further 0.1-2 weight part of aliphatic carboxylic acid ester of polyhydric alcohol. In this manner, antistatic property can be provided to polycarbonate resins even under a low humidity condition without adversely affecting the naturally transparent characteristic of polycarbonate resin.

[0022] Antistatic agents of this invention may be applied within the framework of this invention together with agents of other kinds such as lubricants, antioxidants and ultraviolet light absorbers.

[0023] The invention is described next in terms of particular embodiments of antistatic agents and three particular embodiments of method of application.

Embodiment 1: Antistatic agent with tetrabutyl phosphonium octyl sulfonate and sodium dodecylphenyl sulfonate at weight ratio of 90/10.

Embodiment 2: Antistatic agent with tetrabutyl phosphonium stearyl sulfonate and sodium dodecylphenyl sulfonate at weight ratio of 95/5.

Embodiment 3: Antistatic agent with tetrabutyl phosphonium dodecylphenyl sulfonate and potassium dodecylphenyl sulfonate at weight ratio of 93/7.

Embodiment 4: Antistatic agent with diethyl-dihexyl phosphonium diisopropyl-naphthyl sulfonate and sodium diisopropyl-naphthyl sulfonate at weight ratio of 95/5.

Embodiment 5: Antistatic agent with (1) tetrabutyl phosphonium dodecylphenyl sulfonate, (2) potassium dodecylphenyl sulfonate and (3) diglycerol monostearate at weight ratio $(1)/(2) = 93/7$ and $((1)+(2))/(3) = 50/50$.

Embodiment 6: Antistatic agent with tetrabutyl phosphonium octyl sulfonate and magnesium dodecylphenyl sulfonate at weight ratio of 90/10.

Embodiment 7: Antistatic agent with tetrabutyl phosphonium lauryl sulfonate and calcium dodecylphenyl sulfonate at weight ratio of 95/5.

Embodiment 8: Antistatic agent with tetrabutyl phosphonium dodecylphenyl sulfonate and magnesium dodecylphenyl sulfonate at weight ratio of 90/10.

Embodiment 9: Antistatic agent with diethyl-dihexyl phosphonium diisopropyl-naphthyl sulfonate and magnesium diisopropyl-naphthyl sulfonate at weight ratio of 92/8.

Embodiment 10: Antistatic agent with (1) tetrabutyl phosphonium dodecylphenyl sulfonate, (2) magnesium dodecylphenyl sulfonate and (3) diglycerol monostearate at weight ratio $(1)/(2) = 90/10$ and $((1)+(2))/(3) = 50/50$.

[0024] The three particular embodiments of method of application are as follows:

Embodiment 11: Method of applying each component of the antistatic agents of Embodiments 1-10 at weight ratio of 2 weight parts of their sum to 100 weight parts of polycarbonate resin.

Embodiment 12: Method of applying each component of the antistatic agents of Embodiments 1-10 at weight ratio of 1 weight part of their sum to 100 weight parts of polyethylene terephthalate resin.

Embodiment 13: Method of applying each component of the antistatic agents of Embodiments 1-10 at weight ratio of 3.5 weight parts of their sum to 100 weight parts of polymethyl methacrylate resin.

[0025] Next, the invention will be described by way of test examples but it goes without saying that these examples are not intended to limit the scope of the invention. In what follows, "parts" will mean "weight parts" and "%" will mean "weight %".

Part 1: Preparation of components of antistatic agents

Preparation of phosphonium sulfonates shown by Formula (1)

[0026] Dioctyl-dimethyl phosphonium chloride (323 parts = 1.0 mole) was mixed to sodium cetyl sulfonate (328 parts = 1.0 mole) in a solvent. After sodium chloride thus produced was removed by washing with water, the solvent was distilled away to obtain dioctyl-dimethyl phosphonium cetyl sulfonate (563 parts = 0.95 moles). This will be referred to as antistatic component (Q-1). Components (Q-2) - (Q-7) as summarized in Table 1 were similarly obtained.

Table 1

Phosphonium sulfates shown by Formula (1)					
	A ¹ (group)	R ¹ (group)	R ² (group)	R ³ (group)	R ⁴ (group)
Q-1	cetyl	octyl	octyl	methyl	methyl
Q-2	docosanyl	butyl	butyl	butyl	butyl
Q-3	hexenyl	hydroxyethyl	hydroxyethyl	hydroxyethyl	methyl
Q-4	phenyl	phenyl	phenyl	phenyl	methyl
Q-5	dodecylphenyl	butyl	butyl	butyl	butyl
Q-6	naphthyl	cyanoethyl	cyanoethyl	cyanoethyl	methyl
Q-7	diisopropyl-naphthyl	octyl	octyl	octyl	methyl

Preparation of inorganic sulfonates shown by Formula (2)

[0027] Sodium lauryl sulfonate (270 parts = 0.99 moles) was obtained by neutralizing lauryl sulfonic acid (250 parts = 1.0 mole) with sodium hydroxide (40 parts = 1.0 mole) in a usual manner. This will be referred to as antistatic component (N-1). Components (N-2) - (N-6) as summarized in Table 2 were similarly obtained.

[0028] Calcium lauryl sulfonate (533 parts = 0.99 moles) was obtained by neutralizing lauryl sulfonic acid (500 parts = 2.0 moles) with calcium hydroxide (74 parts = 1.0 mole) in a usual manner. This will be referred to as antistatic component (N-7). Components (N-8) - (N-12) as also summarized in Table 2 were similarly obtained.

Table 2

Inorganic sulfonates shown by Formula (2)		
	A ² (group)	M ⁿ⁺
N-1	lauryl	Na ⁺
N-2	octadecenyl	K ⁺
N-3	phenyl	Na ⁺
N-4	dodecylphenyl	Na ⁺
N-5	naphthyl	K ⁺
N-6	diisopropyl naphthyl	Na ⁺
N-7	lauryl	Ca ⁺⁺
N-8	octadecenyl	Mg ⁺⁺
N-9	phenyl	Ca ⁺⁺
N-10	dodecylphenyl	Mg ⁺⁺
N-11	naphthyl	Ca ⁺⁺
N-12	diisopropyl naphthyl	Mg ⁺⁺

Part 2: Preparation of antistatic agents

[0029] Antistatic agent (P-1) (100 parts) was prepared by mixing dioctyl-dimethyl phosphonium propyl sulfonate (99 parts) and sodium dodecylphenyl sulfonate (1 part). Antistatic agents (P-2) - (P-4), (P-8) and (P-14) - (P-23) were similarly prepared as summarized in Tables 3 and 4.

[0030] Antistatic agent (P-5) (187 parts) was prepared by mixing component (N-2) (189 parts = 0.51 moles) obtained in Part 1 and triphenylmethyl phosphonium chloride (16 parts = 0.05 moles) according to the method described in Japanese Patent Publication Tokkai 2-188593 and removing sodium chloride which was produced. Antistatic agents (P-6) and (P-7) were similarly prepared as summarized also in Table 3.

[0031] Antistatic agent (P-9) (182 parts) was prepared by mixing naphthyl sulfonic acid (155 parts = 0.72 moles), sodium carbonate (30 parts = 0.28 moles) and tricyanoethylmethyl phosphonium hydroxide (34 parts = 0.15 moles) to neutralize according to the method described in Japanese Patent Publication Tokko 47-2234. Antistatic agent (P-10) was similarly prepared as summarized also in Table 3.

[0032] Antistatic agent (P-11) (30 parts) was prepared by mixing 20 parts of (P-3) and 10 parts of glycerol monostearate.

[0033] Antistatic agent (P-12) (20 parts) was prepared by mixing 10 parts of (P-7) and 10 parts of diglycerol monostearate.

[0034] Antistatic agent (P-13) (30 parts) was prepared by mixing 10 parts of (P-10) and 20 parts of pentaerythritol distearate.

[0035] Antistatic agent (P-24) (30 parts) was prepared by mixing 20 parts of (P-16) and 10 parts of glycerol monostearate.

[0036] Antistatic agent (P-25) (20 parts) was prepared by mixing 10 parts of (P-20) and 10 parts of diglycerol monostearate.

[0037] Antistatic agent (P-26) (30 parts) was prepared by mixing 10 parts of (P-23) and 20 parts of pentaerythritol distearate.

Table 3

	Phosphonium sulfonate (Q) shown by Formula (1)					Inorganic sulfonate (N) shown by Formula (2)		Weight ratio (Q)/(N)
	A ¹	R ¹	R ²	R ³	R ⁴	A ²	M ¹⁺	
P-1	PP	OC	OC	MT	MT	DCP	Na ⁺	99/1
P-2	OC	BT	BT	BT	BT	DCP	Na ⁺	90/10
P-3	ST	BT	BT	BT	BT	DCP	Na ⁺	95/5

Table 3 (continued)

	Phosphonium sulfonate (Q) shown by Formula (1)					Inorganic sulfonate (N) shown by Formula (2)		Weight ratio (Q)/(N)
	A ¹	R ¹	R ²	R ³	R ⁴	A ²	M ¹⁺	
P-4	DO	BT	BT	BT	BT	OC	K ⁺	90/10
P-5	OD	PH	PH	PH	MT	OD	K ⁺	15/85
P-6	PH	HE	HE	HE	ET	PH	Na ⁺	50/50
P-7	DCP	BT	BT	BT	BT	DCP	K ⁺	93/7
P-8	DNP	BT	BT	BT	BT	ST	Na ⁺	90/10
P-9	NP	CE	CE	CE	MT	NP	Na ⁺	35/65
P-10	DI	ET	ET	HX	HX	DI	Na ⁺	95/5

Table 4

	Phosphonium sulfonate (Q) shown by Formula (1)					Inorganic sulfonate (N) shown by Formula (2)		Weight ratio (Q)/(N)
	A ¹	R ¹	R ²	R ³	R ⁴	A ²	M ²⁺	
P-14	PP	OC	OC	MT	MT	DCP	Mg ⁺⁺	98/2
P-15	OC	BT	BT	BT	BT	DCP	Mg ⁺⁺	90/10
P-16	LR	BT	BT	BT	BT	DCP	Ca ⁺⁺	95/5
P-17	DO	BT	BT	BT	BT	OC	Ca ⁺⁺	90/10
P-18	OD	PH	PH	PH	MT	OD	Ca ⁺⁺	15/85
P-19	PH	HE	HE	HE	ET	PH	Mg ⁺⁺	50/50
P-20	DCP	BT	BT	BT	BT	DCP	Mg ⁺⁺	90/10
P-21	DNP	BT	BT	BT	BT	ST	Ca ⁺⁺	90/10
P-22	NP	CE	CE	CE	MT	NP	Mg ⁺⁺	35/65
P-23	DI	ET	ET	HX	HX	DI	Mg ⁺⁺	92/8

In Tables 3 and 4:

PP: propyl group
 OC: octyl group
 ST: stearyl group
 LR: lauryl group
 DO: docosanyl group
 OD: octadecenyl group
 PH: phenyl group
 DCP: dodecyl phenyl group
 DNP: dinonyl phenyl group
 DI: diisopropyl naphthyl group
 BT: butyl group
 HE: hydroxyethyl group
 CE: cyanoethyl group
 ET: ethyl group
 HX: hexyl group
 MT: methyl group
 NP: naphthyl group

Part 3 Effects of antistatic agents

Experiment 1

[0038] Polycarbonate resin (100 parts) and antistatic agent (P-1) (1.5 parts) were placed inside a mill (Labo Plastomill

(tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 280°C to obtain a resin composition. The resin composition thus obtained was molded into sheets of thickness 2mm. Specific surface resistance (hereafter abbreviated as "SSR") of these sheets was measured and evaluated as explained below. Their tinting strength (hereafter abbreviated as "TS") and transparency (hereafter abbreviated as "TR") were also observed and evaluated as explained below. This is referred to as Test Example 1. Similar tests were carried out with other antistatic agents embodying this invention (Test Examples 2-26) as well as individual components of these agents (Comparison Examples 1-11). The test results are summarized in Table 5.

Measurement and evaluation of specific surface resistance

[0039] After the sheets produced as above were kept for 24 hours inside an isothermal chamber at a constant humidity (20°C at 45% RH) to adjust their moisture level, their specific surface resistance was measured by means of a super megohm meter (Type SM-8210 produced by Toa Denpa Kogyo, Inc.) under the same environmental condition according to JIS-K6911 and evaluated as follows:

- AAA: Excellent (SSR being smaller than $5 \times 10^{12}\Omega$)
- AA: Good (SSR being larger than $5 \times 10^{12}\Omega$ and smaller than $5 \times 10^{13}\Omega$).
- A: Fair (SSR being larger than $5 \times 10^{13}\Omega$ and smaller than $5 \times 10^{14}\Omega$).
- B: Poor (SSR being larger than $5 \times 10^{14}\Omega$ and smaller than $1 \times 10^{16}\Omega$).
- C: Bad (SSR being larger than $1 \times 10^{16}\Omega$).

Evaluation of tinting strength (TS)

[0040] The sheets, after their specific surface resistance was measured, were observed visually and evaluated as follows:

- AA: Same hue as the blanks which were produced in the same way except no antistatic agent or its component was used.
- A: Slightly stronger hue than the blanks.
- B: Somewhat stronger hue than the blanks.
- C: Significantly stronger hue than the blanks.

Evaluation of transparency "TR"

[0041] The sheets, after their specific surface resistance was measured, were observed visually and evaluated as follows:

- A: Slightly more turbid than the blanks.
- B: Clearly more turbid than the blanks.
- C: Significantly more turbid than the blanks.

Experiment 2

[0042] Polyethylene terephthalate resin (100 parts) and antistatic agent (P-2) (0.6 parts) were placed inside a mill (Labo Plastomill (tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 280°C to obtain another resin composition. The resin composition thus obtained was molded into sheets of thickness 2mm by means of a hot press (produced by Toyo Seiki, Inc.) at 260°C. Specific surface resistance (SSR) and tinting strength (TS) of these sheets were also observed and evaluated as done in Experiment 1 described above. This is referred to as Test Example 27, and similar tests were carried out with other antistatic agents embodying this invention (Test Examples 28-38) as well as with their individual components (Comparison Examples 12-22). The test results are summarized in Table 6.

Experiment 3

[0043] Polymethyl methacrylate resin (100 parts) and antistatic agent (P-3) (1 part) were placed inside a mill (Labo Plastomill (tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 260°C to obtain still another resin composition. The resin composition thus obtained was molded into sheets of thickness 2mm by means of a hot press (produced by Toyo Seiki, Inc.) at 260°C. Specific surface resistance (SSR), tinting strength (TS) and transparency (TR) of these sheets were also observed and evaluated as in Experiment 1 described above. This is referred to as Test

Example 39, and similar tests were carried out with other antistatic agents embodying this invention (Test Examples 40-46) as well as with their individual components (Comparison Examples 23-28). The test results are summarized in Table 7.

Experiment 4

[0044] Polycarbonate resin (100 parts) and antistatic agent components (Q-1) (1.9 parts) and (N-1) (0.1 parts) were placed inside a mill (Labo Plastomill (tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 280°C to obtain still another resin composition. Sheets were produced from this resin composition as above and their specific surface resistance (SSR), tinting strength (TS) and transparency (TR) were also observed and evaluated as in Experiment 1 described above. This is referred to as Test Example 47, and similar tests were carried out with other antistatic agent compositions embodying this invention (Test Examples 48-66). The test results are summarized in Table 8.

Experiment 5

[0045] Polymethyl methacrylate resin (100 parts) and antistatic agent components (Q-1) (1.6 parts) and (N-4) (0.4 parts) were placed inside a mill (Labo Plastomill (tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 280°C to obtain still another resin composition. Sheets were produced from this resin composition as above and their specific surface resistance (SSR), tinting strength (TS) and transparency (TR) were also observed and evaluated as in Experiment 1 described above. This is referred to as Test Example 67, and similar tests were carried out with other antistatic agent compositions embodying this invention (Test Examples 68-74). The test results are summarized in Table 9.

Experiment 6

[0046] Polyethylene terephthalate resin (100 parts) and antistatic agent components (Q-1) (1.9 parts) and (N-1) (0.1 parts) were placed inside a mill (Labo Plastomill (tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 280°C to obtain still another resin composition. Sheets were produced from this resin composition as above and their specific surface resistance (SSR) and tinting strength (TS) were also observed and evaluated as in Experiment 1 described above. This is referred to as Test Example 75, and similar tests were carried out with other antistatic agent compositions embodying this invention (Test Examples 76, 78 and 87-90). The test results are summarized in Table 10.

Experiment 7

[0047] Polyethylene resin (100 parts) and antistatic agent components (Q-1) (1.6 parts) and (N-4) (0.4 parts) were placed inside a mill (Labo Plastomill (tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 180°C to obtain still another resin composition. Sheets were produced from this resin composition as above and their specific surface resistance (SSR) and tinting strength (TS) were also observed and evaluated as in Experiment 1 described above. This is referred to as Test Example 79, and similar tests were carried out with other antistatic agent compositions embodying this invention (Test Examples 80-82 and 91-94). The test results are summarized also in Table 10.

Experiment 8

[0048] Polycaprolactam resin (100 parts) and antistatic agent components (Q-1) (1.9 parts) and (N-4) (0.1 parts) were placed inside a mill (Labo Plastomill (tradename), produced by Toyo Seiki, Inc.) and kneaded for 5 minutes at 280°C to obtain still another resin composition. Sheets were produced from this resin composition as above and their specific surface resistance (SSR) and tinting strength (TS) were also observed and evaluated as in Experiment 1 described above. This is referred to as Test Example 83, and similar tests were carried out with other antistatic agent compositions embodying this invention (Test Examples 84-86 and 95-98). The test results are summarized also in Table 10.

[0049] As can be clear from these results, this invention has the merit of providing superior antistatic property to synthetic polymer materials without adversely affecting their natural hue or transparency even under a low humidity condition.

Table 5

		Antistatic agents and components				Evaluations		
		Q/N	[Q+N]	[N]	[E]	SSR	TS	TR
Test Examples								
1	(P-1)	99/1	1.5	0.015	1.0^{*1} 1.0^{*2} 2.0^{*3} 1.0^{*1} 1.0^{*2} 2.0^{*3}	A	AA	AA
2	(P-2)	90/10	2.0	0.20		AA	AA	A
3	(P-3)	95/5	2.0	0.10		AA	AA	AA
4	(P-4)	90/10	1.5	0.15		AA	AA	A
5	(P-5)	15/85	0.2	0.17		AA	AA	A
6	(P-6)	50/50	0.4	0.20		AA	AA	A
7	(P-7)	93/7	1.0	0.07		AAA	AA	AA
8	(P-8)	90/10	2.0	0.20		AA	AA	A
9	(P-9)	35/65	0.3	0.195		AA	AA	A
10	(P-10)	95/5	1.8	0.09		AA	AA	AA
11	(P-11)	98/2	2.0	0.04		AAA	AA	AA
12	(P-12)	93/7	1.0	0.07		AAA	AA	AA
13	(P-13)	95/5	1.0	0.05		AAA	AA	AA
14	(P-14)	98/2	1.5	0.03		A	AA	AA
15	(P-15)	90/10	2.0	0.20		A	AA	A
16	(P-16)	95/5	2.0	0.10		AA	AA	AA
17	(P-17)	90/10	1.5	0.15		A	AA	AA
18	(P-18)	20/80	0.2	0.17		A	AA	AA
19	(P-19)	50/50	0.8	0.40		AA	AA	A
20	(P-20)	90/10	1.0	0.10		AAA	AA	AA
21	(P-21)	90/10	2.0	0.20		A	AA	AA
22	(P-22)	35/65	1.0	0.325		AA	AA	A
23	(P-23)	92/8	1.8	0.144		AA	AA	AA
24	(P-24)	95/5	2.0	0.10		AAA	AA	AA
25	(P-25)	90/10	1.0	0.10		AAA	AA	AA
26	(P-26)	92/8	1.0	0.08		AAA	AA	AA
Comparison Examples								
1	(Q-1)	100/0	2.0	0		C	A	AA
2	(Q-2)	100/0	2.0	0		C	A	AA
3	(Q-3)	100/0	4.0	0		B	C	AA
4	(Q-4)	100/0	4.0	0		B	C	AA
5	(Q-5)	100/0	2.0	0		C	A	AA
6	(Q-6)	100/0	2.0	0		C	A	AA
7	(Q-7)	100/0	2.0	0		C	A	AA
8	(N-1)	0/100	2.0	2.0		B	B	C
9	(N-2)	0/100	2.0	2.0		B	B	C
10	(N-7)	0/100	2.0	2.0		C	C	C
11	(N-10)	0/100	3.0	3.0		C	B	C

In Fig. 5 and hereafter:

Q: phosphonium sulfonate shown by Formula (1)
 N: inorganic sulfonate shown by Formula (2)
 Q/N: weight ratio of Q and N
 [Q+N]: total weight part of Q and N against 100 parts of resin

EP 1 000 969 B1

[N]: weight part of N against 100 parts of resin
 [E]: weight part of aliphatic carboxylic acid ester of polyhydric alcohol used against 100 parts of resin
 *1: glycerol monostearate
 *2: diglycerol monostearate
 *3: pentaerythritol distearate

Table 6

		Antistatic agents and components		Evaluations	
		Q/N	[Q+N]	SSR	TS
Test Examples					
27	(P-2)	90/10	0.6	AA	AA
28	(P-3)	95/5	1.0	AA	AA
29	(P-4)	90/10	1.0	AA	AA
30	(P-7)	93/7	1.0	AAA	AA
31	(P-9)	35/65	2.0	AA	AA
32	(P-10)	95/5	2.0	AA	AA
33	(P-15)	90/10	2.0	AA	AA
34	(P-16)	95/5	2.0	AA	AA
35	(P-17)	90/10	1.5	AA	AA
36	(P-20)	90/10	1.0	AAA	AA
37	(P-22)	35/65	3.0	AA	AA
38	(P-23)	92/8	1.8	AA	AA
Comparison Examples					
12	(Q-1)	100/0	2.0	C	A
13	(Q-2)	100/0	2.0	C	A
14	(Q-3)	100/0	2.0	C	A
15	(Q-4)	100/0	2.0	C	A
16	(Q-5)	100/0	2.0	C	A
17	(Q-6)	100/0	2.0	C	A
18	(Q-7)	100/0	4.0	B	C
19	(N-1)	0/100	2.0	B	B
20	(N-2)	0/100	2.0	B	B
21	(N-7)	0/100	2.0	B	B
22	(N-10)	0/100	2.0	C	B

Table 7

		Antistatic agents and components		Evaluations		
		Q/N	[Q+N]	SSR	TS	TR
Test Examples						
39	(P-3)	95/5	1.0	AA	AA	AA
40	(P-6)	50/50	2.0	AA	AA	A
41	(P-7)	93/7	2.0	AAA	AA	AA
42	(P-10)	95/5	2.0	AA	AA	AA
43	(P-16)	95/5	1.0	AA	AA	AA
44	(P-19)	50/50	4.0	AA	AA	A
45	(P-20)	90/10	2.0	AAA	AA	AA
46	(P-23)	92/8	2.0	AA	AA	AA

EP 1 000 969 B1

Table 7 (continued)

Comparison Examples		Antistatic agents and components		Evaluations		
23	(Q-1)	100/0	2.0	C	A	AA
24	(Q-4)	100/0	2.0	C	A	AA
25	(Q-5)	100/0	4.0	A	C	AA
26	(Q-7)	100/0	2.0	C	A	AA
27	(N-1)	0/100	2.0	B	B	C
28	(N-7)	0/100	2.0	C	B	B

Table 8

		Antistatic agent components				Method of mixing	Evaluations		
		Q/N	[Q+N]	[N]	[E]		SSR	TS	TR
Test Examples									
47	Q-1/N-1	95/5	2.0	0.10		a	AA	AA	AA
48	Q-2/N-4	90/10	0.8	0.08		a	AA	AA	AA
49	Q-3/N-2	35/65	0.3	0.195		b	AA	AA	A
50	Q-4/N-3	50/50	0.4	0.20		c	AA	AA	A
51	Q-5/N-4	95/5	2.0	0.10		a	AAA	AA	AA
52	Q-6/N-5	70/30	0.5	0.15		c	AA	AA	A
53	Q-7/N-6	90/10	1.0	0.10		b	AA	AA	AA
54	Q-2/N-1	95/5	1.0	0.05		a	AAA	AA	AA
55	Q-5/N-4	95/5	1.5	0.075		a	AAA	AA	AA
56	Q-7/N-6	95/5	2.0	0.10		a	AAA	AA	AA
57	Q-1/N-7	95/5	2.0	0.10	a	AA	AA	AA	
58	Q-2/N-10	90/10	0.8	0.08	a	AA	AA	AA	
59	Q-3/N-8	35/65	0.3	0.195	b	A	AA	AA	
60	Q-4/N-9	50/50	0.8	0.40	c	AA	AA	A	
61	Q-5/N-10	90/10	2.0	0.20	a	AAA	AA	AA	
62	Q-6/N-11	70/30	1.0	0.30	c	AA	AA	A	
63	Q-7/N-12	90/10	1.0	0.10	b	AA	AA	AA	
64	Q-2/N-7	95/5	1.0	0.05		a	AAA	AA	AA
65	Q-5/N-10	95/5	1.5	0.075		a	AAA	AA	AA
66	Q-7/N-12	95/5	2.0	0.10		a	AAA	AA	AA

In Fig.8 and hereafter:

- a: Resin, phosphonium sulfonate shown by Formula (1), inorganic sulfonate shown by Formula (2) and aliphatic carboxylic acid ester of polyhydric alcohol (if used) were mixed simultaneously in a mixer and kneaded together.
- b: After resin and phosphonium sulfonate shown by Formula (1) were mixed simultaneously in a mixer and kneaded together, inorganic sulfonate shown by Formula (2) was added and further kneaded together.
- c: After resin and inorganic sulfonate shown by Formula (2) were mixed simultaneously in a mixer and kneaded together, phosphonium sulfonate shown by Formula (1) was added and further kneaded together.

Table 9

		Antistatic agent components		Method of mixing	Evaluations			
		Q/N	[Q+N]		SSR	TS	TR	
5	Test Examples							
10	67	Q-1/N-4	80/20	2.0	a	AA	AA	AA
	68	Q-2/N-1	95/5	2.0	b	AA	AA	AA
	69	Q-5/N-4	90/10	2.0	c	AAA	AA	AA
	70	Q-7/N-6	90/10	1.5	c	AA	AA	AA
	71	Q-1/N-10	80/20	2.0	a	AA	AA	AA
15	72	Q-2/N-7	85/15	2.0	b	AA	AA	AA
	73	Q-5/N-10	85/15	2.0	c	AAA	AA	AA
	74	Q-7/N-12	90/10	1.5	c	AA	AA	AA

Table 10

20			Antistatic agent components		Method of mixing	Resin type	Evaluations	
			Q/N	[Q+N]			SSR	TS
	Test Examples							
25	75	Q-1/N-1	95/5	2.0	a	PET	AA	AA
	76	Q-2/N-4	80/20	2.0	a	PET	AA	AA
	77	Q-5/N-4	95/5	2.0	b	PET	AAA	AA
	78	Q-7/N-6	80/20	2.0	c	PET	AA	AA
	79	Q-1/N-4	80/20	1.0	a	PE	AA	AA
30	80	Q-2/N-6	90/10	1.0	a	PE	AA	AA
	81	Q-5/N-4	95/5	2.0	b	PE	AAA	AA
	82	Q-7/N-1	80/20	2.0	c	PE	AA	AA
	83	Q-1/N-4	95/5	2.0	a	PCL	AA	AA
	84	Q-2/N-1	80/20	2.0	b	PCL	AA	AA
35	85	Q-5/N-4	90/10	1.0	c	PCL	AAA	AA
	86	Q-7/N-6	80/20	2.0	c	PCL	AA	AA
	87	Q-1/N-7	95/5	2.0	a	PET	AA	AA
	88	Q-2/N-10	80/20	2.0	a	PET	AA	AA
	89	Q-5/N-10	90/10	2.0	b	PET	AAA	AA
40	90	Q-7/N-12	80/20	2.0	c	PET	AA	AA
	91	Q-1/N-10	80/20	1.0	a	PE	AA	AA
	92	Q-2/N-12	90/10	1.0	a	PE	AA	AA
	93	Q-5/N-10	90/10	2.0	b	PE	AAA	AA
	94	Q-7/N-7	80/20	2.0	c	PE	AA	AA
45	95	Q-1/N-10	95/5	2.0	a	PCL	AA	AA
	96	Q-2/N-7	80/20	2.0	b	PCL	AA	AA
	97	Q-5/N-10	90/10	1.0	c	PCL	AAA	AA
	98	Q-7/N-12	80/20	2.0	c	PCL	AA	AA
	50							

In Table 10:


PET: polyethylene terephthalate resin

PE: polyethylene resin


PCL: polycaprolactam resin

Claims

1. An antistatic agent for synthetic polymer materials, said antistatic agent comprising phosphonium sulfonate shown by Formula (1) and inorganic sulfonate shown by Formula (2) wherein Formula (1) is




and Formula (2) is




where A^1 and A^2 are each independently an alkyl group with 1-36 carbon atoms, an alkenyl group with 4-24 carbon atoms, a phenyl group, a phenyl group substituted by an alkyl group with 1-18 carbon atoms, a naphthyl group or a naphthyl group substituted by an alkyl group with 1-18 carbon atoms; R^1 , R^2 , R^3 and R^4 are each independently an aliphatic or aromatic hydrocarbon group with 1-18 carbon atoms or a hydrocarbon group substituted by a hydroxyl or cyano group; M^{n+} is an alkali metal cation if $n = 1$ and an alkaline-earth metal cation if $n = 2$; and $n = 1$ or 2 .

2. The antistatic agent of claim 1 further comprising an aliphatic carboxylic acid ester of polyhydric alcohol.
3. The antistatic agent of claim 1 containing said phosphonium sulfonate shown by Formula (1) and said inorganic sulfonate shown by Formula (2) at a weight ratio of 99/1 - 5/95.
4. The antistatic agent of claim 2 containing said phosphonium sulfonate shown by Formula (1) and said inorganic sulfonate shown by Formula (2) at a weight ratio of 99/1 - 5/95, the weight ratio of the sum of said phosphonium sulfonate shown by Formula (1) and said inorganic sulfonate shown by Formula (2) with respect to said aliphatic carboxylic acid ester of polyhydric alcohol being 95/5 - 10/90.
5. The antistatic agent of claim 3 or claim 4 wherein A^1 is selected from the group consisting of alkyl groups with 6-22 carbon atoms, phenyl groups substituted by an alkyl group with 2-12 carbon atoms and naphthyl groups substituted by an alkyl group with 2-12 carbon atoms.
6. The antistatic agent of any of claims 3 to 5 wherein R^1 , R^2 , R^3 , and R^4 are each a butyl group.
7. The antistatic agent of any of claims 3 to 6 wherein A^2 is selected from the group consisting of alkyl groups with 6-22 carbon atoms, phenyl groups substituted by an alkyl group with 2-12 carbon atoms and naphthyl groups substituted by an alkyl group with 2-12 carbon atoms.
8. A method of providing antistatic characteristic to a synthetic polymer material by applying antistatic agent components, said method comprising the step of providing said synthetic polymer material with phosphonium sulfonate shown by Formula (1) and inorganic sulfonate shown by Formula (2) at weight ratio of 99/1 - 5/95 wherein Formula (1) is



and Formula (2) is




where A¹ and A² are each independently an alkyl group with 1-36 carbon atoms, an alkenyl group with 4-24 carbon atoms, a phenyl group, a phenyl group substituted by an alkyl group with 1-18 carbon atoms, a naphthyl group or a naphthyl group substituted by an alkyl group with 1-18 carbon atoms; R¹, R², R³ and R⁴ are each independently an aliphatic or aromatic hydrocarbon group with 1-18 carbon atoms or a hydrocarbon group substituted by a hydroxyl or cyano group; Mⁿ⁺ is alkali metal cation if n = 1 and alkaline-earth metal cation if n = 2; and n = 1 or 2.


9. The method of claim 8 further comprising the step of providing said synthetic polymer material also with aliphatic carboxylic acid ester of polyhydric alcohol such that the weight ratio of the sum of said phosphonium sulfonate shown by Formula (1) and said inorganic sulfonate shown by Formula (2) with respect to said aliphatic carboxylic acid ester of polyhydric alcohol is 95/5 - 10/90.
10. The method of claim 8 or claim 9 wherein A¹ is selected from the group consisting of alkyl groups with 6-22 carbon atoms, phenyl groups substituted by an alkyl group with 2-12 carbon atoms and naphthyl groups substituted by an alkyl group with 2-12 carbon atoms.
11. The method of any of claims 8 to 10 wherein R¹, R², R³, and R⁴ are each a butyl group.
12. The method of any of claims 8 to 11 wherein A² is selected from the group consisting of alkyl groups with 6-22 carbon atoms, phenyl groups substituted by an alkyl group with 2-12 carbon atoms and naphthyl groups substituted by an alkyl group with 2-12 carbon atoms.
13. The method of any of claims 8 to 12 wherein a total of 0.1-10 weight parts of said antistatic agent components is applied to 100 weight parts of said synthetic polymer material.

Patentansprüche

1. Antistatisches Mittel für synthetische Polymermaterialien, wobei das antistatische Mittel das in Formel (1) gezeigte Phosphoniumsulfonat und das in Formel (2) gezeigte anorganische Sulfonat aufweist, wobei Formel 1 lautet:



und Formel (2) lautet:




worin A¹ und A² jedes unabhängig eine Alkyl-Gruppe mit 1 bis 36 Kohlenstoffatomen sind, eine Alkenyl-Gruppe mit 4 bis 24 Kohlenstoffatomen, eine Phenyl-Gruppe sind, eine Phenyl-Gruppe, substituiert durch eine Alkyl-Gruppe mit 1 bis 18 Kohlenstoffatomen, eine Naphthyl-Gruppe oder eine Naphthyl-Gruppe, substituiert durch eine Alkyl-Gruppe mit 1 bis 18 Kohlenstoffatomen; R¹, R², R³ und R⁴ sind jeweils unabhängig eine aliphatische oder aromatische Kohlenwasserstoff-Gruppe mit 1 bis 18 Kohlenstoffatomen oder eine Kohlenwasserstoff-Gruppe, substituiert durch eine Hydroxyl- oder eine Cyano-Gruppe; Mⁿ⁺ ist ein Alkalimetall-Kation, wenn n=1 gilt und ein Erdalkalimetall-Kation, wenn n=2 gilt; und n = 1 oder 2.


2. Antistatisches Mittel nach Anspruch 1, ferner aufweisend einen aliphatischen Carbonsäureester eines mehrwertigen Alkohols.
3. Antistatisches Mittel nach Anspruch 1, enthaltend das in Formel (1) gezeigte Phosphoniumsulfonat und das in Formel (2) gezeigte anorganische Sulfonat in einem Gewichtsverhältnis von 99/1 bis 5/95.
4. Antistatisches Mittel nach Anspruch 2, enthaltend das in Formel (1) gezeigte Phosphoniumsulfonat und das in Formel (2) gezeigte anorganische Sulfonat in einem Gewichtsverhältnis von 99/1 bis 5/95, wobei das Gewichtsverhältnis der Summe des in Formel (1) gezeigten Phosphoniumsulfonats und des in Formel (2) gezeigten anor-

ganischen Sulfonats in Bezug auf den aliphatischen Carbonsäureester eines mehrwertigen Alkohols 95/5 bis 10/90 beträgt.

- 5 5. Antistatisches Mittel nach Anspruch 3 oder 4, worin A¹ ausgewählt ist aus der Gruppe, bestehend aus Alkyl-Gruppen mit 6 bis 22 Kohlenstoffatomen, Phenyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen, und Naphthyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen.
- 10 6. Antistatisches Mittel nach einem der vorgenannten Ansprüche 3 bis 5, worin R¹, R², R³ und R⁴ jeweils eine Butyl-Gruppe sind.
7. Antistatisches Mittel nach einem der vorgenannten Ansprüche 3 bis 6, worin A² ausgewählt ist aus der Gruppe, bestehend aus Alkyl-Gruppen mit 6 bis 22 Kohlenstoffatomen, Phenyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen, und Naphthyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen.
- 15 8. Verfahren zum Ausstatten eines synthetischen Polymaterials mit antistatischen Eigenschaften durch Aufbringen von Komponenten eines antistatischen Mittels, welches Verfahren den Schritt des Ausstattens des synthetischen Polymaterials mit dem in Formel (1) gezeigten Phosphoniumsulfonat und dem in Formel (2) gezeigten anorganischen Sulfonat in einem Gewichtsverhältnis von 99/1 bis 5/95 umfasst, wobei Formel 1 lautet:




und Formel (2) lautet:




- 25 30 35 40 45 50 55
9. Verfahren nach Anspruch 8, ferner umfassend den Schritt des Ausstattens des synthetischen Polymaterials auch mit aliphatischem Carbonsäureester eines mehrwertigen Alkohols derart, dass das Gewichtsverhältnis der Summe des in Formel (1) gezeigten Phosphoniumsulfonats und des in Formel (2) gezeigten anorganischen Sulfonats in Bezug auf den aliphatischen Carbonsäureester eines mehrwertigen Alkohols 95/5 bis 10/90 beträgt.
10. Verfahren nach Anspruch 8 oder 9, wobei A¹ ausgewählt ist aus der Gruppe, bestehend aus Alkyl-Gruppen mit 6 bis 22 Kohlenstoffatomen, Phenyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen, und Naphthyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen.
11. Verfahren nach einem der Ansprüche 8 bis 10, worin R¹, R², R³ und R⁴ jeweils eine Butyl-Gruppe sind.
12. Verfahren nach einem der Ansprüche 8 bis 11, worin A² ausgewählt ist aus der Gruppe, bestehend aus Alkyl-Gruppen mit 6 bis 22 Kohlenstoffatomen, Phenyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen, und Naphthyl-Gruppen, substituiert durch eine Alkyl-Gruppe mit 2 bis 12 Kohlenstoffatomen.
13. Verfahren nach einem der Ansprüche 8 bis 12, worin insgesamt 0,1 bis 10 Gewichtsteile der Komponenten des antistatischen Mittels auf 100 Gewichtsteile des Polymaterials aufgetragen werden.

Revendications

1. Agent antistatique pour des matériaux polymères synthétiques, ledit agent antistatique comprenant un sulfonate de phosphonium montré par la Formule (1) et un sulfonate inorganique montré par la Formule (2), dans lequel la




et la Formule (2) est:




où A¹ et A² sont chacun indépendamment un groupe alkyle avec 1-36 atomes de carbone, un groupe alcényle avec 4-24 atomes de carbone, un groupe phényle, un groupe phényle substitué par un groupe alkyle avec 1-18 atomes de carbone, un groupe naphthyle ou un groupe naphthyle substitué par un groupe alkyle avec 1-18 atomes de carbone; R¹, R², R³ et R⁴ sont chacun indépendamment un groupe hydrocarbure aliphatique ou aromatique avec 1-18 atomes de carbone ou un groupe hydrocarbure substitué par un groupe hydroxyle ou cyano; Mⁿ⁺ est un cation de métal alcalin si n = 1 et un cation de métal alcalino-terreux si n = 2; et n = 1 ou 2.

2. Agent antistatique suivant la revendication 1, comprenant en outre un ester d'acide carboxylique aliphatique d'un alcool polyhydrique.
3. Agent antistatique suivant la revendication 1, contenant ledit sulfonate de phosphonium montré par la Formule (1) et ledit sulfonate inorganique montré par la Formule (2) à un rapport en poids de 99/1-5/95.
4. Agent antistatique suivant la revendication 2, contenant ledit sulfonate de phosphonium montré par la Formule (1) et ledit sulfonate inorganique montré par la Formule (2) à un rapport en poids de 99/1-5/95, le rapport en poids de la somme dudit sulfonate de phosphonium montré par la Formule (1) et dudit sulfonate inorganique montré par la Formule (2) relativement audit ester d'acide carboxylique aliphatique d'alcool polyhydrique étant de 95/5-10/90.
5. Agent antistatique suivant la revendication 3 ou la revendication 4, dans lequel A¹ est choisi dans le groupe constitué de groupes alkyles avec 6-22 atomes de carbone, de groupes phényles substitués par un groupe alkyle avec 2-12 atomes de carbone et de groupes naphthyles substitués par un groupe alkyle avec 2-12 atomes de carbone.
6. Agent antistatique suivant l'une quelconque des revendications 3 à 5, dans lequel R¹, R², R³ et R⁴ sont chacun un groupe butyle.
7. Agent antistatique suivant l'une quelconque des revendications 3 à 6, dans lequel A² est choisi dans le groupe constitué de groupes alkyles avec 6-22 atomes de carbone, de groupes phényles substitués par un groupe alkyle avec 2-12 atomes de carbone et de groupes naphthyles substitués par un groupe alkyle avec 2-12 atomes de carbone.
8. Procédé pour donner une caractéristique antistatique à un matériau polymère synthétique en appliquant des composants de l'agent antistatique, ledit procédé comprenant l'étape d'apport audit matériau polymère synthétique d'un sulfonate de phosphonium montré par la Formule (1) et d'un sulfonate inorganique montré par la Formule (2) à un rapport en poids de 99/1-5/95, dans lequel la Formule (1) est:



et la Formule (2) est:



5

où A¹ et A² sont chacun indépendamment un groupe alkyle avec 1-36 atomes de carbone, un groupe alcényle avec 4-24 atomes de carbone, un groupe phényle, un groupe phényle substitué par un groupe alkyle avec 1-18 atomes de carbone, un groupe naphthyle ou un groupe naphthyle substitué par un groupe alkyle avec 1-18 atomes de carbone; R¹, R², R³ et R⁴ sont chacun indépendamment un groupe hydrocarbure aliphatique ou aromatique avec 1-18 atomes de carbone ou un groupe hydrocarbure substitué par un groupe hydroxyle ou cyano; Mⁿ⁺ est un cation de métal alcalin si n = 1 et un cation de métal alcalino-terreux si n = 2; et n = 1 ou 2.

10

15

9. Procédé suivant la revendication 8, comprenant en outre l'étape d'apport audit matériau polymère synthétique également d'un ester d'acide carboxylique aliphatique d'un alcool polyhydrique de sorte que le rapport en poids de la somme dudit sulfonate de phosphonium montré par la Formule (1) et dudit sulfonate inorganique montré par la Formule (2) relativement audit ester d'acide carboxylique aliphatique d'alcool polyhydrique est de 95/5-10/90.

20

10. Procédé suivant la revendication 8 ou la revendication 9, dans lequel A¹ est choisi dans le groupe constitué de groupes alkyles avec 6-22 atomes de carbone, de groupes phényles substitués par un groupe alkyle avec 2-12 atomes de carbone et de groupes naphtyles substitués par un groupe alkyle avec 2-12 atomes de carbone.

11. Procédé suivant l'une quelconque des revendications 8 à 10, dans lequel R¹, R², R³ et R⁴ sont chacun un groupe butyle.

25

12. Procédé suivant l'une quelconque des revendications 8 à 11, dans lequel A² est choisi dans le groupe constitué de groupes alkyles avec 6-22 atomes de carbone, de groupes phényles substitués par un groupe alkyle avec 2-12 atomes de carbone et de groupes naphtyles substitués par un groupe alkyle avec 2-12 atomes de carbone.

30

13. Procédé suivant l'une quelconque des revendications 8 à 12, dans lequel un total de 0,1-10 parties en poids desdits composants de l'agent antistatique est appliqué à 100 parties en poids dudit matériau polymère synthétique.

35

40

45

50

55